

Fire-Resistant Geopolymer Composites

Two main projects

GEO-COMPOSITE

fire resistant aircraft composites and cabin interior applications,
fire-resistant composites for public transportation, offshore oil platforms,
military vehicles.

GEO-STRUCTURE

External repair and structural retrofit for aging infrastructure
and aging buildings

in collaboration with:

R.E. Lyon, Federal Aviation Administration Technical Center, Fire Research Section, USA

U. Sorathia, Carderock Division, Naval Surface Warfare Center, USA

P.N. Balaguru and A. Foden, Dept. Civil Engineering, Rutgers the State University
of New Jersey, USA

J. Davidovits and M. Davidovics, Geopolymere, Saint-Quentin, France

presented at ICCI'96, Tuscon, Arizona, USA, January 15-17



FIRE RESPONSE OF GEOPOLYMER STRUCTURAL COMPOSITES

Richard E. Lyon
Fire Research Section
Federal Aviation Administration Technical Center
Atlantic City International Airport, NJ 08405

Usman Sorathia
Carderock Division, Naval Surface Warfare Center
Annapolis, MD

P.N. Balaguru and Andrew Foden
Department of Civil Engineering
Rutgers the State University of New Jersey

Joseph Davidovits and Michel Davidovics
GEOPOLYMER
St.-Quentin, FRANCE

Abstract: The fire response of a potassium aluminosilicate matrix (GEOPOLYMER) carbon fiber composite was measured and the results compared to organic matrix composites being used for infrastructure and transportation applications. At irradiance levels of 50 kW/m² typical of the heat flux in a well developed fire, glass- or carbon-reinforced polyester, vinylester, epoxy, bismaleimide, cyanate ester, polyimide, phenolic, and engineering thermoplastic laminates ignited readily and released appreciable heat and smoke, while carbon-fiber reinforced GEOPOLYMER composites did not ignite, burn, or release any smoke even after extended heat flux exposure. The GEOPOLYMER matrix carbon fiber composite retains sixty-three percent of its original 245 MPa flexural strength after a simulated large fire exposure.

Keywords: Aluminosilicate, ceramic composite, cone calorimeter, fire, fire barrier, fire hazard, flame spread, flammability, flexural strength, GEOPOLYMER, heat release, smoke.

Introduction


Infrastructure in the United States such as bridges are degrading due to the corrosion of steel-reinforced concrete by salty water and deicing compounds [1]. As a result a number of research programs have been initiated to study the feasibility of using plastic reinforced, continuous glass-, carbon-, and aramid-fiber reinforced composites to replace the steel rebar in concrete bridges and highways. Carbon fibers may be uniquely suited to these applications because of an outstanding combination of chemical and fatigue resistance [2]. Another application for continuous fiber composites in infrastructure, already well underway in Japan, is the wrapping of concrete columns to reinforce new construction and damaged bridges and buildings in earthquake prone areas. In this application, particularly for exposed, interior building columns, flammability is a serious concern. The flammability of organic polymer matrix, fiber-reinforced composites also limits the use of these materials in offshore oil platforms, military vehicles [3] and public transportation [4] where fire endurance and fire hazard are important design considerations.

Although significant progress has been made in recent years to develop new, high temperature, thermoxidatively stable fibers from boron, silicon carbide, and ceramics [5], parallel work on high temperature/fire resistant matrix materials to bind the fibers has not kept pace. At the present time, affordable, low-temperature processable matrix materials for fire resistant composites are unavailable since most organic polymers soften and ignite at temperatures of 400-600°C characteristic of fuel fire exposure conditions. This susceptibility to fire currently limits the use of polymer composites in infrastructure precluding any useful advantage in specific strength/stiffness and corrosion resistance compared to steel or concrete.

The Federal Aviation Administration has recently initiated a research program to develop low-cost, environmentally-friendly, fire resistant matrix materials for use in aircraft composites and cabin interior applications [6]. The flammability requirement for new materials is that they withstand a 50 kW/m² incident heat flux characteristic of a fully-developed aviation fuel fire penetrating a cabin opening, without propagating the fire into the cabin compartment [7]. The goal of the program is to eliminate cabin fire as cause of death in aircraft accidents. However, voluntary adoption of the new materials technology by aircraft and cabin manufacturers requires that it be cost effective to install and use, so it is expected that these new aircraft materials will be broadly applicable in transportation and infrastructure where a high degree of intrinsic fire resistance is needed at low to moderate cost. To this end we are evaluating a new, low-cost, inorganic polymer derived from the naturally occurring geological materials- silica and alumina- hence the name GEOPOLYMER

Materials

The GEOPOLYMER matrix resin being evaluated for structural composites is a potassium aluminosilicate, or poly(sialate-siloxo), with the general chemical structure:



where, $z \gg n$. This particular resin hardens to an amorphous or glassy material at moderate temperatures and is one of a family of inorganic GEOPOLYMER materials described previously [8,9]. Cross-ply [0/90] composites were fabricated by hand rolling the caustic aqueous liquid resin into a flat weave carbon fabric and air drying 30 seconds at 80°C to remove residual moisture and develop tack. Approximately 25 plies were then cut, stacked, and cured in a vacuum bag at 80°C in a heated press with 0.3 MPa pressure for three hours. The panels were then removed from the vacuum bag and dried for an additional 12 hours at 80°C or until constant weight was achieved. Final thickness of the crossply laminates was a uniform 5.6-mm and the density was 1.85 g/cm³. Visual inspection of cut edges revealed that the laminates were substantially void free. No effort was made to determine the fiber volume fraction of the GEOPOLYMER laminates.

Organic matrix crossply laminates of polyester (PE), vinylester (VE), epoxy (EP), cyanate ester (CE), bismaleimide (BMI), PMR-15 polyimide (PI), and phenolic (PH), thermoset resins as well as thermoplastic polyphenylene sulfide (PPS), polyetheretherketone (PEEK), polyetherketoneketone (PEKK), polyarylsulfone (PAS), and polyethersulfone (PES) resin matrices were prepared from commercial S-glass, E-glass or carbon fabric prepregs. The details of material composition and fabrication have been described elsewhere [10-12]. Some of the phenolic laminates were hand impregnated [13] and contained only about 34 volume percent fiber compared to a nominal 60 percent fiber volume for all of the commercial prepreg materials. The density of these cured laminates ranged from about 1.55 to about 1.98 g/cm³ at the nominal 60 volume percent carbon and glass fiber loading, respectively.

Methods

Ignitability, Heat Release, and Smoke (ASTM E-1354): Peak heat release rate, 300-second average heat release rate, total heat release, mass loss during burning, ignitability (time-to-ignition), and the specific extinction area of smoke produced were measured in an oxygen consumption calorimeter employing a conical radiant heater to provide 50 kW/m² of radiant energy to the surface of a 10-cm by 10-cm sample having a nominal thickness 6-mm. The sample is positioned horizontally on a weighing device with a spark igniter 2.54-cm above the surface to ignite combustible vapors (piloted ignition). The mass flowrate of air past the burning sample is measured as well as the amount of oxygen consumed from the air stream by the combustion process and these measurements are used to calculate the heat release rate (HRR) of the burning material using a factor of 13.1 kJ of heat produced per gram of oxygen consumed [14].

Flame Spread Index (ASTM E-162-83): Flame spread across a surface is one measure of the propensity of a material to propagate a fire. Downward flame spread was measured after ignition of a 15-cm by 46-cm sample by a radiant heat source. Only the combustible organic matrix composites were tested in this procedure as the GEOPOLYMER sample would not support flaming combustion.

Residual Flexural Strength (ASTM D-790): Specimens were tested for flexural strength before and after the fire test to determine the residual strength of the composite panels after fire exposure. Specimens having dimensions 7.6-cm by 7.6-cm were exposed to a 25 kW/m² radiant heat source for a duration of 20 minutes according to ASTM E-662 protocol for smoke generation in a flaming mode. The panels were reclaimed and 5 coupons, 1.27-cm wide by 7.6-cm long were cut from each for flexural testing on a universal testing machine. The GEOPOLYMER composites were not subjected to the ASTM E-662 protocol because they would not burn. Instead a more severe test was used wherein panels were exposed to an 800°C oxidizing environment for 60 minutes [15], which is the equivalent of a 75 kW/m² radiant energy exposure in air compared to the 25 kW/m² exposure for the organic matrix composites. The original sample thickness was used to calculate the residual flexural strength for all samples after the fire test.

Results and Discussion

Table 1 summarizes all of the cone calorimeter data for the composite specimens. Individual values for percent weight loss during the fire test, time to ignition, peak heat release rate, 300-second average heat release rate, total heat released per unit area, and specific extinction area of smoke are reported for each material. Average values of these fire parameters were calculated for families of the organic materials grouped together according to chemistry (condensation/phenolics, addition/thermosets), physical properties (engineering thermoplastics), or end-use applications (high temperature/advanced thermosets). It is seen that this somewhat arbitrary grouping leads to variations within groups which can be greater than the variation between groups. However the averages are fairly representative of each type of material, and it is clear that the GEOPOLYMER composite is non-combustible while all of the organic polymer matrix composites support flaming combustion. It was noted that the GEOPOLYMER resin became white (crystallized) after fire exposure but did not ignite or smoke even after ten minutes in the cone calorimeter.

It is important to try to understand how or if the fire parameters in Table 1, measured in a small scale bench test, relate to the actual fire hazard of a composite material in the use environment. This is a very difficult task and it is important to realize that no single parameter will provide the best estimation of the fire hazard of a material because the hazard depends to a large extent on where and how the material is used (e.g., enclosed space, open space, structural, non-structural, etc.).

Table 1.
Fire Calorimetry Data for Crossply Laminates at 50 kW/m² Irradiance [10-12]

RESIN	FIBER	Weight Loss	Time to Ignition	300s Peak HRR	Total Average HRR	Heat Release	Smoke
		%	Seconds	kW/m ²	kW/m ²	MJ/m ²	m ² /kg
Isophthalic polyester	Glass	-	77	198	120	-	378
Vynil Ester	Glass	-	78	222	158	-	861
Vynil Ester	Glass	26	74	119	78	25	1721
Epoxy	Glass	-	105	178	98	30	580
Epoxy	Glass	19	18	40	2	29	566
Epoxy	Glass	28	49	181	108	39	1753
Epoxy	Glass	22	50	294	135	43	1683
Epoxy	Carbon	24	94	171	93	-	-
THERMOSETS		24	68	175	99	33	1077
Cyanate Ester	Glass	22	58	130	71	49	898
PMR-15 polyimide	Glass	11	175	40	27	21	170
Bismaleimide	Glass	25	141	176	161	60	546
ADVANCED THERMOSETS		24	124	115	86	43	538
Phenolic	Glass	-	210	47	38	14	176
Phenolic	Glass	12	214	81	40	17	83
Phenolic	Glass	6	238	82	73	15	75
Phenolic	Glass	10	180	190	139	43	71
Phenolic	Glass	3	313	132	22	12	143
Phenolic	Carbon	28	104	177	112	50	253
Phenolic	Carbon	9	187	71	41	14	194
PHENOLICS		11	206	111	66	23	142
Polyphenylenesulfide	Glass	13	244	48	28	39	690
Polyphenylenesulfide	Carbon	16	173	94	70	26	604
Polyarylsulfone	Carbon	3	122	24	8	1	79
Polyethersulfone	Carbon	-	172	11	6	3	145
Polyetheretherketone	Carbon	2	307	14	8	3	69
Polyetherketoneketone	Carbon	6	223	21	10	15	274
ENGINEERING PLASTICS		8	207	35	22	15	310
GEOPOLYMER		0		0	0	0	0

It has been suggested that heat release rate of a material measured in small scale tests under simulated radiant exposure conditions is the single most important parameter in characterizing the hazard of a material in a fire [16]. Recently, it was shown that a combined parameter which is the ratio of the peak heat release rate to the time to ignition, also known as the flame propagation index (FPI) or flashover parameter, is a more accurate predictor of time-to-flashover in both room and aircraft compartment fires because it more accurately accounts for thickness effects of the material [17]:

$$\text{Flame Propagation Index (FPI)} = \frac{\text{Peak Heat Release Rate (kW/m}^2\text{)}}{\text{Time-to-ignition (seconds)}} \quad (2)$$

Flashover is a phenomenon unique to compartment fires where incomplete combustion products accumulate at the ceiling and ignite causing total involvement of the compartment materials and signaling the end to human survivability. Consequently, in a compartment fire the time to flashover is the time available for escape and this is the single most important factor in determining the fire hazard of a material or set of materials in a compartment fire. The Federal Aviation Administration has used the time-to-flashover of

materials in aircraft cabin tests as the basis for a heat release and heat release rate acceptance criteria for cabin materials for commercial aircraft [6]. Figure 1 shows the calculated time to flashover of the 6-mm thick composite material groups from Table 1 if they were used as wall linings in an 8 ft x 12 ft room which is 8 feet high. The equation used to calculate the time to flashover from the peak heat release rate /time to ignition ratio (FPI from Table 1 is [17]

$$\text{Time-to-flashover (sec)} = 991 - 629 \log_{10} \text{FPI} \quad (3)$$

Equation 3 provided the best fit ($r^2 = 0.94$) to all of the EURIFIC full scale fire test data [18] for 13 different lining materials obtained according to ISO 9705 corner wall/room fire test using the 100/300 ignition option (100 kW fire for 10 minutes + 300 kW fire for additional 10 minutes) in the corner of a 3.6-m long x 2.4-m wide by 2.4-m high room. For comparison to the predicted behavior of the composite materials in Figure 1, materials in the ISO 9705 test with 10-12 minute flashover times include a melamine high pressure laminate on non-combustible board, steel faced polymeric foam with mineral wool backing, fire-retardant PVC on gypsum wallboard, fire retardant particle board, and a fire retardant textile on gypsum wallboard.

The calculated values for time-to-flashover of organic and GEOPOLYMER composites in a full scale room test shown in Figure 1 provide a qualitative ranking of the fire hazard of these materials in a compartment. The engineering thermoplastics are predicted not to reach flashover during the 20 minute ignition period but could generate appreciable smoke, while the GEOPOLYMER composite will never ignite, reach flashover, or generate any smoke in a compartment fire. It is possible that the actual time to flashover of the continuous fiber reinforced composite laminates listed in Table 1 would be significantly different from the calculated values displayed in Figure 1 and full-scale validation tests of these materials are planned.




Figure 1: Predicted time to flashover in ISO 9705 corner/room fire test with various structural composites as wall materials

The flame spread index provides a relative measure of the speed at which the flame front of a burning composite travels. Consequently the flame spread index provides a qualitative ranking of the rate of fire growth in an open environment. Figure 2 shows a plot of the ratio of the peak heat release rate / time-to-ignition (FPI) from Table 1 for selected materials which were also tested for flame spread index. The correlation is seen to be very good between the flame propagation index determined in the bench scale cone calorimeter test and the measured ASTM E-162 flame spread index for these cross-ply composite laminates. According to this plot, the GEOPOLYMER composite would have a flame spread index of zero, indicating that the GEOPOLYMER composite would be an excellent fire barrier.




Figure 2. Flame Propagation Index at 50 kW/m² incident flux versus Flame Spread Index for a number of glass-reinforced organic polymer composites.

Perhaps the most important fire response parameter for infrastructure applications is the residual strength of the composite after fire exposure. Comparison of the composite resin categories on the basis of percent residual flexural strength retained after the fire exposure is shown in Figure 3. The values represent a combined average for the thermoset (vinylester, epoxy), advanced thermoset (BMI, PI), phenolic, and engineering thermoplastic (PPS, PEEK). As mentioned previously, the carbon fiber reinforced GEOPOLYMER crossply laminate was subjected to a much more severe thermal environment (800°C/75 kW/m²) than the organic composites but still retains 63% of its original 245 MPa flexural strength. By way of comparison the original flexural strength of the carbon fiber reinforced phenolic resin crossply laminate was 283 MPa.




Figure 3. Residual Flexural Strength of Cross-ply Laminates after Fire Exposure

Conclusions

Carbon fiber reinforced potassium aluminosilicate resin (GEOPOLYMER) composites are non-combustible structural materials which are suitable for infrastructure applications where a high degree of fire resistance is needed at low to moderate cost. Carbon fabric reinforced GEOPOLYMER crossply laminates fabricated at 80°C have comparable strength to fabric reinforced organic resin composites and better strength retention after fire exposure. It is anticipated that loadbearing capability during fire exposure, where temperatures reach several hundred degrees Centigrade, will be significantly higher than organic resin composites which soften and lose nearly all of their compressive strength at these temperatures.

References

1. Leonard, L. (1990). "Rebuilding the Infrastructure with Advanced Composites," *Advanced Composites*, 5 (3), pp. 43-47
2. Walton, J.M. and Yeung, Y.T.C. (1986). "Fatigue Performance of Structural Strands of Pultruded Composite Rods," *J.Inst.Mech.Eng.*, C286/86, pp. 315-320
3. Demarco, R.A. (1991). "Composite Applications at Sea: Fire Related Issues," *Proc. 36th Int'L SAMPE Symposium*, April 15-18, pp. 1928-1938
4. Hathaway, W.T. (1991). "Fire Safety in Mass Transit Vehicle Materials," *Proc. 36th Int'l. SAMPE Symposium*, April 15-18, pp. 1900-1915
5. Engineered Materials Handbook, Vol. 1. , COMPOSITES, ASM International, Metals Park, OH, 1987
6. Lyon, R.E. (1995). "Fire Safe Aircraft Cabin Materials," in *Fire and Polymers*, ACS Symposium Series Number 599, G.L. Nelson, ed., American Chemical Society, Washington, D.C., p. 618
7. Lyon, R.E. (1994). "Advanced Fire Safe Aircraft Materials Research Program," Technical Report DOT/FAA/CT-94/60
8. Davidovits, J. (1991). "GEOPOLYMERS: Inorganic Polymeric New Materials," *J. Thermal Analysis*, 37, pp. 1633-1756
9. Davidovits, J., and Davidovics, M (1991). "GEOPOLYMER: Ultra-High Temperature Tooling Material for the Manufacture of Advanced Composites," *Proc. 36th Int'l SAMPE Symposium*, pp. 1939-1949
10. Scudamore, M.J. , Briggs, P.J. and Prager, F.H. (1991). "Cone Calorimetry-A Review of Tests Carried Out on Plastics for the Association of Plastics Manufacturers in Europe," *Fire and Materials*, 15, pp. 65-84
11. Sorathia, U, Dapp, T., and Kerr, J. (1991). "Flammability Characteristics of Composites for Shipboard and Submarine Internal Applications," *Proc. 36th Int'l SAMPE Symposium*, pp. 1868
- 12.. Sorathia, U, Rollhauser, C.M., and Hughes, W.A. (1992). "Improved Fire Safety of Composites for Naval Applications," *Fire and Materials*, 16, pp. 119-125
13. Sorathia, U., Telegadas, H, and Beck, C. (1994). "Mechanical and Flammability Characteristics of Phenolic Composites for Naval Applications," *Proc. 39th Int'l SAMPE Symposium*, pp. 1940
14. Babrauskas, V. (1992) "Heat of Combustion and Potential Heat," in *Heat Release in Fires*, Chapter 8, Elsevier Applied Science, New York, pp. 207-223
15. Foden, A. J., Lyon, R.E., Balaguru, P.N., and Davidovits, J., (1996) "High Temperature Inorganic Resin for Use in Fiber Reinforced Composites," *Proceedings of the First International Conference on Composites in Infrastructure (ICCI 96)*, Jan. 15-17, Tucson, Arizona
16. Babrauskas, V. and Peacock, R.D. (1992). "Heat Release Rate: Single Most Important Variable in Fire Hazard," *Fire Safety Journal*, 18, pp. 255-272
17. Hirschler, M. M. (1995) in *Fire and Polymers*, ACS Symposium Series Number 599, G.L. Nelson, ed., American Chemical Society, Washington, D.C.
18. Sundstrom, B. (1991). "Classification of Wall and Ceiling Linings," *Proceedings of the EURIFIC Seminar*, Copenhagen, Denmark, September 11-12